

TEKNOFLOR®

HIGH PERFORMANCE FLOORING



USN
009-26
COMPLIANT

RARE PLANK HPD™

LUXURY VINYL PLANK • HIGH PERFORMANCE DESIGN • USA MADE



89006RP Light Maple



89005RP Adobe



89010RP Greige



89008RP Sand



89016RP Driftwood



89007RP Sisal



89004RP Light Oak



89009RP Latte



89011RP Wheat



89017RP Weathered



89003RP
American Walnut



89020RP Desert



89021RP Rojo



89002RP Red Oak



89022RP Burnt Sienna



89001RP English Oak



89012RP Aged Copper



89013RP Black Walnut



89014RP Lunar



89015RP Ash



89018RP Patina



89019RP Ebony



TEKNOFLOR® RARE PLANK HPD™

COMMERCIAL LUXURY VINYL PLANK • HIGH PERFORMANCE DESIGN

PRODUCT DATA

STANDARD SPECIFICATION	ASTM F1700 - Meets or exceed requirements	DIMENSIONS	7.09" x 47.24" (180mm x 1200mm)
CLASSIFICATION	Class III, Type B	PCS / CARTON	15 Pcs
BACKING CLASS	Class A	SQ. FT / CARTON	34.88 Sq. Ft.
COMPOSITION	Virgin PVC, No outside recycled content and Phthalate Free	WEAR LAYER THICKNESS	28 mil (0.7mm)
TOP COAT	HP Urethane Coating with Ceramic Bead	OVERALL THICKNESS	3.0mm (0.118")
WARRANTY	20 Years		

PERFORMANCE SPECIFICATIONS	TEST METHOD	STANDARD REQUIREMENT	RESULT
CHEMICAL RESISTANCE	ASTM F925	0- No change or 1 - Slight Change	0 - No Change
HEAT STABILITY COLOR CHANGE	ASTM F1514	$\Delta E < 8.0$ avg. @ 7 days	Passes
LIGHT STABILITY COLOR CHANGE	ASTM F1515	$\Delta E < 8.0$ avg. @ 300 hrs.	Passes
SHORT TERM INDENTATION	ASTM F1914	avg. $< 8.0\%$ @ 140 lbs.	avg. 4.8% 0.005"
STATIC LOAD LIMIT	ASTM F970	250 psi ≤ 0.005 " Residual Indentation	Exceeds Requirements 1,200 psi at maximum limit
FLOORSCORE	Certified		SCS-FS-03430
HEAVY METALS	ASTM F963		No concern with heavy metal content
ABRASION RESISTANCE	ASTM D4060	H18 Wheel & 1 kg mass applied	$\geq 25,000$ cycles to see effect on design layer
CASTOR CHAIR TEST	Castor Chair Test	150 lbs. / Rating Scale 1-5 / 5-No Change / 1 - Severe Change	25,000 cycles - 4.5 - Slight Change
REACH -Substances of Very High Concern (SVHC)	Test for EU REACH Chemicals of Concern	SVHC's tested must be less than 0.1% by product weight	Passes

SAFETY PERFORMANCE	TEST METHOD	STANDARD REQUIREMENT	RESULT
STATIC COEFFICIENT OF FRICTION (SCOF)	D2047	≥ 0.5 SCOF Dry	≥ 0.6 SCOF Dry
DYNAMIC COEFFICIENT OF FRICTION (DCOF)	ANSI B101.3	Low/Acceptable/High Traction - Wet DCOF	Acceptable Traction Wet DCOF
CRITICAL RADIANT FLUX	E648	Class I: ≥ 0.45 w/cm ² Class II: ≥ 0.22 w/cm ²	Class I
SMOKE GENERATION	E662	< 450 Flaming	< 450 Flaming & Non-Flaming

APPROVED FOR EMERGENCY EGRESS AREAS - NFPA 101 AND NFPA 99

Natural variation and random characteristics will be seen from plank to plank within each carton to emulate true natural wood floors. This product is manufactured in the United States

PHILIP "P.J." HUGHES
Fed Gov / DoD / GSA Account Manager
SDVOSB GSA SCHEDULE • GS-27F-0036V
VAMC VIP Verified • www.vip.vetbiz.gov
CAGE Code: 4RRA8
PH: 937.829.8316
pjhughes@shannonspecialtyfloors.com



Schedule
GS-27F-0504H • GS-27F-0036V
GS-27F-0015V

